



Analyse Data sheet

<i>Slack Wax (light)</i>		
Specification	result	Method
Color	0.5 - 3	ASTM D 1500
Oil content WT%	3 - 8 %	ASTM D 721
Kinematic Viscosity @ 100 °C(cSt)	3 - 6 %	ASTM D 445
Melting point °C	55 - 60 °C	ASTM D 87

<i>Slack Wax (heavy)</i>		
Specification	result	Method
Color	0.5 - 1.5	ASTM D 1500
Oil content WT%	7 - 11 %	ASTM D 721
Kinematic Viscosity @ 100 °C(cSt)	6 – 7.5 %	ASTM D 445
Melting point °C	56 - 65 °C	ASTM D 87