



**Middle East
Sofia Trade**



info@sofia-trading.com
sofiatrade@yahoo.com



www.sofia-trading.com



1th floor, NO29, hasan Moqhadas,
Ahmad Ghasir AVE., Argentina
square., Tehran, Iran.



0098(21)88509011-14

Analyse Data sheet

PE WAX 915F					
Softening point	Penetration index (D1321)	Flash Point	Viscosity @140°C ,Cp	Appearance/ characteristics	Applications
105-110 °C	3-6	>170°C	20-50	Super dry Snow white, high Softening point. Good hardness, non-toxic , good thermal stability , low volatility	Hot melt High Quality (PVC Stabilizer), High quality filler & color masterbatch



**Middle East
Sofia Trade**



info@sofia-trading.com
sofiatrade@yahoo.com



www.sofia-trading.com



1th floor, NO29, hasan Moqhadas,
Ahmad Ghasir AVE., Argentina
square., Tehran, Iran.



0098(21)88509011-14

Analyse Data sheet

PE WAX 920F					
Softening point	Penetration index (D1321)	Flash Point	Viscosity @140°C ,Cp	Appearance/ characteristics	Applications
105-110 °C	3-4	>180°C	20-40	Super dry Snow white Flakes , high Softening point Good hardness, non-toxic , good thermal stability , low volatility	Hot melt Adhesive, High Quality PVC Stabilizer , high Quality filler & Color masterbatch



**Middle East
Sofia Trade**



info@sofia-trading.com
sofiatrade@yahoo.com



www.sofia-trading.com



11th floor, NO29, hasan Moqhadas,
Ahmad Ghasir AVE., Argentina
square., Tehran, Iran.



0098(21)88509011-14

Analyse Data sheet

PE WAX 925					
Softening point	Penetration index (D1321)	Flash Point	Viscosity @140°C ,Cp	Appearance/ characteristics	Applications
105-110 °C	3-4	>200°C	20-50	Super dry white Beads, high softening point. Good hardness, non-toxic , good thermal stability , low volatility	Hot melt High Quality (PVC Stabilizer), High Quality filler & Color masterbatch



**Middle East
Sofia Trade**



info@sofia-trading.com
sofiatrade@yahoo.com



www.sofia-trading.com



1th floor, NO29, hasan Moqhadas,
Ahmad Ghasir AVE., Argentina
square., Tehran, Iran.



0098(21)88509011-14

Analyse Data sheet

PE WAX 970					
Softening point	Penetration index (D1321)	Flash Point	Viscosity @140°C ,Cp	Appearance/ characteristics	Applications
85-90 °C	20-30	130°C<	10-40	Snow white Flakes , free of black spots	PVC Point & filler masterbatch



**Middle East
Sofia Trade**



info@sofia-trading.com
sofiatrade@yahoo.com



www.sofia-trading.com



1th floor, NO29, hasan Moqhadas,
Ahmad Ghasir AVE., Argentina
square., Tehran, Iran.



0098(21)88509011-14

Analyse Data sheet

PE WAX 980					
Softening point	Penetration index (D1321)	Flash Point	Viscosity @140°C ,Cp	Appearance/ characteristics	Applications
100-105 °C	5-8	140°C<	10-20	Dry and snow white flakes , free of black spots	PVC, high quality filler & color masterbatch